



Contribution ID: 305

Type: Poster Presentation

Thermoluminescence of annealed synthetic quartz

Tuesday, 30 June 2015 16:10 (1h 50m)

Abstract content (Max 300 words) Formatting & Special chars

Thermoluminescence from synthetic quartz annealed at 1000° for 10 minutes has been studied. The sample was exposed to beta irradiation of 10Gy then heated at linear heating rate of 1°/s. The glow curve obtained has three peaks. One known as the main peak, has the highest intensity component while the other two have weaker intensities. This study focuses on the properties of this main peak whose peak position was found at 76°. Kinetic analyses were carried out to determine kinetic parameters such as activation energy (E), frequency factor (s) and order of kinetics (b); using a variety of methods namely initial rise, peak shape and variable heating rate. Observations indicate that the behaviour of this peak is consistent with first-order kinetics. The activation energy was found to be about 1.17eV using the initial rise method and 0.89eV using the variable heating rate method. The frequency factor, a measure of the number of times a trapped electron attempts to escape from its trap was found to be about 4×10^{11} Hz. Further work which includes dose dependence study of the main peak is in progress.

Key words: Thermoluminescence, synthetic quartz, annealed, glow curve.

Apply to be considered for a student award (Yes / No)?

YES

Level for award (Hons, MSc, PhD, N/A)?

MSc

Main supervisor (name and email) and his / her institution

Prof CHITHAMBO Makaiko, M.Chithambo@ru.ac.za, Rhodes University

Would you like to submit a short paper for the Conference Proceedings (Yes / No)?

YES

Please indicate whether this abstract may be published online (Yes / No)

YES

Primary author: Mr MTHWESI, zuko (Rhodes University)

Co-author: Prof. CHITHAMBO, Makaiko (Rhodes University)

Presenter: Mr MTHWESI, zuko (Rhodes University)

Session Classification: Poster1

Track Classification: Track A - Division for Physics of Condensed Matter and Materials