



Contribution ID: 55

Type: Oral Presentation

Effects of impurities and defects on the performances of synthetic diamond crystals when used as radiation sensors for medical applications

Tuesday, 10 July 2012 11:00 (20 minutes)

Abstract content
 (Max 300 words)

Diamond is attractive for medical applications due to its remarkable dosimetric properties such as bio-compatibility, high sensitivity, high spatial resolution, non-toxicity, and more cost effective as it was shown in a previous study that a single synthetic diamond probe could perform effectively in both low-energy X-rays and megavoltage electron beams. The dosimetric performance of a diamond crystal to radiation is well recognised to be dependent on the types of defects and impurity levels within the crystal, however to date their influence on the performance of synthetic diamond crystals when subjected to low-energy X-rays and high-energy electron therapy beams has not been fully investigated. This study was therefore aimed at evaluating the dosimetric performances of synthetic diamond crystals when used as radiation sensors for both radiation types by highlighting some of the defect/impurity types that either enhance or degrade crystal performance in order to select suitable crystals. The sensitivities of synthetic diamond crystals of various types (HPHT and CVD diamond crystals of optical grade (OG) and detector grade (DG)) were evaluated and compared based on their defect/impurity levels. The crystals were characterised by Raman spectroscopy and Electron spin resonance. Linearity measurements with dose were verified both for X-rays and electron beams. The results of the study showed that the HPHT and OG diamonds had much higher levels of single substitutional nitrogen (Ns) impurities and were less sensitive compared to DG diamonds. The sensitivities of the diamond crystals to radiation were found to vary strongly with defect density and impurity levels. The sensitivities of the diamond crystals were largely influenced, in particular by Ns impurities which act as recombination centres and degrade crystal performance in this study suggesting that Ns levels ought to be the foremost criteria used in the selection of sensor material. As DG CVD diamonds have very low Ns impurities such crystals ought to be the radiation sensors of choice for medical applications.

Apply to be
 consider for a student
 award (Yes / No)?

Yes

Level for award
 (Hons, MSc,
 PhD)?

PhD

Main supervisor (name and email)
and his / her institution

T.L. Nam; E-mail address: Tom.Nam@wits.ac.za Institution:University of the Witwatersrand.

**Would you like to
 submit a short paper
 for the Conference
 Proceedings (Yes / No)?**

Yes

Primary author: Mr ADE, Nicholas (School of Physics, Radiation and Health Physics Unit, DST/NRF Centre of Excellence in Strong Materials, University of the Witwatersrand, Private Bag 3, Wits 2050, Johannesburg, and the National Research Foundation of South Africa.)

Co-authors: Mr MHLANGA, Hamilton (Department of Radiation Sciences, Division of Medical Physics, Charlotte Maxeke Johannesburg Academic Hospital, Private Bag X39, Johannesburg, 2000, South Africa.); Prof. NAM, Tom (School of Physics, Radiation and Health Physics Unit, DST/NRF Centre of Excellence in Strong Materials, University of the Witwatersrand, Private Bag 3, Wits 2050, Johannesburg, and the National Research Foundation of South Africa.)

Presenter: Mr ADE, Nicholas (School of Physics, Radiation and Health Physics Unit, DST/NRF Centre of Excellence in Strong Materials, University of the Witwatersrand, Private Bag 3, Wits 2050, Johannesburg, and the National Research Foundation of South Africa.)

Session Classification: Applied Physics Forum

Track Classification: Track F - Applied Physics