



Contribution ID: 259

Type: Oral Presentation

Investigating hydrogen induced Ti₃Al embrittlement in Ti-6Al-4V using TEM

Thursday, 6 July 2023 10:00 (20 minutes)

Temporary hydrogen alloying (THA) can refine coarse-grained as-cast Ti-6Al-4V microstructures and improve tensile strength. However, it can also reduce the tensile ductility to severe embrittlement because of hydrogen promoted titanium aluminide (Ti₃Al) precipitation.[1] The effect of oxygen concentration above a 0.33 wt.% threshold on Ti₃Al promotion is known.[2] The effect of residual hydrogen concentration above a 150-ppm threshold on Ti-6Al-4V embrittlement is also known.[3] Less Known is the effect of hydrogen on the promotion of Ti₃Al precipitation, and the effect of precipitated Ti₃Al on tensile ductility. This study investigates hydrogen promoted Ti₃Al precipitation, and its effects on the tensile ductility of hydrogenated-dehydrogenated (HDH) Ti-6Al-4V.

A hydrogenation-dehydrogenation (HDH) treatment was used to refine a coarse-grained Ti-6Al-4V microstructure with the intention of optimizing its tensile strength and ductility. Microstructure evolution was characterized using X-ray diffraction (XRD), electron backscatter diffraction (EBSD), energy dispersive spectroscopy (EDS) and transmission electron microscopy (TEM). Oxygen and hydrogen concentrations were quantified using inert gas fusion (IGF).

The results indicate that HDH treatment does not refine the coarse network of prior beta grains, but it alters the coarse Widmanstätten microstructure by nucleating submicron beta grains within the individual lamellae. The HDH modified microstructure had higher ultimate tensile strength (UTS) in the order of 100 MPa. The dehydrogenation temperature affected tensile ductility; the lowest dehydrogenation temperature (675 °C) had the highest ductility loss in the order of 75%. Increasing the dehydrogenation temperature recovered ductility until full ductility was recovered at 750°C. The ductility loss was not caused by residual hydrogen or oxygen but was caused by the embrittling effect of hydrogen induced Ti₃Al which remains in the microstructure even after hydrogen removal, and only completely dissolves at a Ti₃Al solvus temperature of 750 °C. The results demonstrate that HDH treatment alters the initial coarse-grained Ti-6Al-4V microstructure to extents that significantly improve strength, but it also promotes Ti₃Al precipitation and its concomitant embrittlement. To improve ductility, the dehydrogenation treatment should be controlled to optimize Ti₃Al dissolution.

References

1. V. Vilane, R. Knutsen, and J. Westraadt: 'Tensile property and microstructure assessment of hydrogen treated Ti-6Al-4V alloy', Mater. Charact., 2022, 184, 111698.
2. M. Yan, W. Xu, M. Dargusch, H. Tang, M. Brandt, and M. Qian: 'Review of effect of oxygen on room temperature ductility of titanium and titanium alloys', Powder Metall., 2014, 57(4), 251-257.
3. W. Kerr, P. Smith, M. Rosenblum, F. Gurney, Y. Mahajan, and L. Bidwell: 'Hydrogen as an alloying element in titanium (hydrovac)', Titanium, 1980, 80, 2477-2486.

Apply to be considered for a student ; award (Yes / No)?

n/a

Level for award;(Hons, MSc, PhD, N/A)?

n/a

Primary authors: VILANE, Velile (Nelson Mandela University); KNUTSEN, Robert (UCT EMU); WES-TRAADT, Johan (Nelson Mandela University)

Presenter: VILANE, Velile (Nelson Mandela University)

Session Classification: Physics of Condensed Matter and Materials Track 1

Track Classification: Track A - Physics of Condensed Matter and Materials