

The joint virtual event of the African Light Source AfLS-2024 (7<sup>th</sup>) and the African Physical Society AfPS2024



Contribution ID: 205

Type: not specified

## Synthesis and characterization of Iron tungstate Nanoparticles as a Photocatalyst and Nano-adsorbent

Monday, 18 November 2024 15:15 (15 minutes)

Synthesis and characterization of Iron tungstate Nanoparticles as a Photocatalyst and Nano-adsorbent O.J. Ajala<sup>1,3</sup>, J.O. Tijani<sup>1,3</sup>, R.B Salau<sup>1</sup>, A.S. Abdulkareem<sup>1,2</sup> 1 Department of Chemistry, Federal University of Technology, P. M. B. 65, Bosso Campus, Minna, Niger state, Nigeria.

2 Department of Chemical Engineering, Federal University of Technology, P. M. B. 65, Gidan Kwano Campus, Minna, Niger State, Nigeria.

3 Nanotechnology Research group, Africa Center of Excellence for Mycotoxin and Food Safety, Federal University of Technology, Minna, P. M. B. 65, Niger State, Nigeria.

Abstract

Iron tungstate (FeWO4) nanoparticles were synthesized using a simple sol-gel method, employing sodium tungstate dihydrate and iron(II) sulfate as precursors, with distilled water serving as the solvent. The synthesized nanoparticles underwent a thorough characterization process utilizing various techniques, including Fourier-transform infrared (FTIR) spectroscopy, high-resolution scanning electron microscopy (HRSEM), high-resolution transmission electron microscopy (HRTEM), energy-dispersive X-ray spectroscopy (EDX), X-ray diffraction (XRD), and Brunauer-Emmett-Teller (BET) nitrogen adsorption-desorption analysis.

FTIR spectroscopy revealed key vibrational modes: peaks at 771 cm–1 and 948 cm–1 were attributed to O–W–O vibrations and W–O bond stretching, respectively. Additionally, a peak at 567 cm–1 corresponded to Fe–O bending vibrations, while peaks at 3423 cm–1 and 1620 cm–1 were assigned to H–O–H stretching modes and bending vibrations, indicating the presence of free or adsorbed water. HRSEM and HRTEM analyses confirmed that the nanoparticles had an aggregated, spherical morphology. Furthermore, XRD analysis demonstrated the formation of a highly crystalline monoclinic phase of FeWO4 under optimal synthesis conditions: a solution pH of 7, a reaction temperature of 30°C, and a stirring speed of 500 rpm. This comprehensive characterization underscores the successful synthesis of FeWO4 nanoparticles and highlights their potential for various applications across multiple fields.

Primary author: AJALA, Oluwaseun (Federal University of Technology Minna, Nigeria)

**Co-authors:** Prof. TIJANI, Jimoh Oladejo (Federal University of Technology Minna, Nigeria); Prof. ABDULKA-REEM, A.S (Federal University of Technology Minna, Nigeria); Prof. SALAU, Rasaq (Federal University of Technology Minna, Nigeria)

Presenter: AJALA, Oluwaseun (Federal University of Technology Minna, Nigeria)

Session Classification: AfLS Contribution

Track Classification: AfLS