



Contribution ID: 327

Type: **Poster Presentation**

## Interaction of tungsten (W) film with glassy carbon

Wednesday, 5 July 2017 17:10 (1h 50m)

Thin film of tungsten (W) was deposited on glassy carbon (GC) substrate using a magnetron sputtering system. The as-deposited samples were annealed under vacuum at temperatures ranging from 600 to 1000 oC for 1hr. The interaction in the interface of W and GC was investigated Rutherford backscattering spectroscopy (RBS) and scanning electron microscopy (SEM). RUMP software was used to simulate the RBS spectra. The thickness of W thin film deposited, atomic composition of deposited layer and the reaction zone (RZ) were deduced from the RUMP results. W-GC interaction became pronounced at annealing temperature from 800 oC and increased progressively up to the highest annealing temperature. The surface morphology of the diffusion couples were examined on SEM. The as-deposited sample possessed a smooth uniform layer of W film while the annealed samples showed a progressive increase in grain size with increased annealing temperature. The atomic composition profile reveals the detailed extent of intermixing and diffusion of the atomic species at the elevated temperatures.

Keywords: tungsten, glassy carbon, interaction, annealing, RBS, RUMP, SEM

**Apply to be considered for a student award (Yes / No)?**

Yes

**Level for award (Hons, MSc, PhD, N/A)?**

PhD

**Main supervisor (name and email) and his / her institution**

Prof. J.B. Malherbe, Johan.Malherbe@up.ac.za  
University of Pretoria, South Africa.

**Would you like to submit a short paper for the Conference Proceedings (Yes / No)?**

Yes

**Primary author:** Mr INNOCENT, Audu (University of Pretoria)

**Co-authors:** Dr NJOROGE, Eric (University of Pretoria); Prof. MALHERBE, Johan (University of Pretoria); Dr HLATSHWAYO, Thulani (University of Pretoria)

**Presenter:** Mr INNOCENT, Audu (University of Pretoria)

**Session Classification:** Poster Session 2

**Track Classification:** Track A - Division for Physics of Condensed Matter and Materials